Horse HM-RB16

Unidirectional Carbon Fiber Rebar For Strengthening

Description

HM-RB16 is a high strength, high modulus unidirectional carbon fiber reinforce polymer(CFRP) for structural strengthening. It is bonded onto the structure as external reinforcement using HM-120CP epoxy resin as the

Application Range

Load Increase

Increased live loads in warehouses
Increased traffic volumes on bridges
Installation of heavy machinery in industrial buildings
Vibrating structures
Changes of building utilization

■ Seismic Reinforcement

Concrete column wrapping, beam strengthening, wall strengthening, slab strengthening

Masonry walls reinforcement■ Damage to Structural Parts

Aging of construction materials

Fire

Vehicle impact

■ Change of Structural System

Removal of walls or columns

Removal of slab sections for openings

Design or Construction Defects

Lack of reinforcing bars

Lack of member cross section

■ Improve Structural State

Reduce the deformation

Reduce the stress of the original structure

The crack reinforcement



- **Product Characteristic** High strength, high toughness, high modulus
 - Soft and flexible, light self weight, easy to install
 - Long shelf life and aging resistance
 - High temperature resistance
 - Acid, alkali & salt resistance
 - Seismic resistance
 - Environmental-friendly
 - Can be used for shear strengthening, confinement strengthening, flexural strengthening

Horse Advantage

Aviation Grade Yarn

Imported aviation grade raw material, excellent quality and stable performance.

■ World Leading Production Line

Germany imported intelligent production line. Point to point active weft insertion. No damage to the yarn during the weaving process.

excellent flatness enable epoxy easy to penetrate, hence high bonding strength can be achieved

Patented Tension Controling System

Our own developed whole process tension controling system. It ensures the constant tension, low dispersion.

■ Large output and Timely Delivery

100 thousand meters annual output.

Package

This product is rolled into a ring and uses a belt to bind. The length of the rebar is 1m, 3m or according to the request, the diameters are 8mm, 10mm,12mm and 16mm or according to the request



Basic Information

Model HM-RB16

Appreance Black laminate

Length 1m, 3m or custimized

Diameter 16mm

Shelf Life 50 years

Storage Conditions Store in dry conditions at 40°F to 95°F (4°C to 35°C)

Braiding 0° (Unidirectional)

Performance indexes

Tensile Strength	
Mean Value	3.19×10^5 psi (2200 MPa)
Design Value	2.90×10^5 psi (2000 MPa)
Tensile Elastic Modulus	
Mean Value	2.39×10^7 psi (1.65×10^5 MPa)
Design Value	2.32×10^7 psi (1.6×10^5 MPa)
Elongation	1.80%
Thickness	1.2mm
Temperature Resistance	>300°F (>150°C)
Fiber volume content	≥65%
Density	0.058 lbs./in3 (1.6g/cm3)

Construction Process



- 1. Setting out according to designing;
- 2. Polish the surface of concrete surface to remove painting of the surface, blow out the floating dust with compressed air;
- 3. Prepare ingredients: agitate component A and B evenly in packaging bucket by weighting in accordance with the weight ratio A: B = 2:1;
- 4. Installing: Past the above mixed glue compounds onto the surface of carbon fiber rebar evenly, please avoid bubbles;
- 5. Anchorage: paste the carbon fiber rebar onto the concrete surface and fixed with steel strip, remove excessive glue compounds around, and fix With Steel framework;
- 6. Maintenance: conservation time should be no less than 24 hours at room temperature.

Points for Attention

The construction workers should take necessary protective measures such as wearing masks, gloves, goggles etc. Pay attention to fire prevention and maintain good ventilation on site.

Carbon fiber material is conductive, be careful to the electrical equipments around.

For more information, please visit our website at www.horseen.com





